



SEM-WOOD

WOOD FILLER PASTE READY-TO-USE SURFACE FILLER INTERIOR-EXTERIOR

- + LITTLE SHRINKAGE
- + VERY HIGH-QUALITY FINISH
- + EASY TO SAND

TECHNICAL DEFINITION.

Surface filler for treating small holes and cracks in wood.

COMPOSITION AND APPEARANCE.

Water, mineral filler, emulsion resin, dispersant and various additives.

The paste is beige.

ACCEPTED SUBSTRATES.

All types of wood.

COVERING.

All types of paint, varnish and wood stain.

DOCUMENTS TO CONSULT.

- DTU 59.1: Building painting work
- EN 16566: paint plasters for interior work

TECHNICAL CHARACTERISTICS.

- Second application: 12-24 hours, depending on the work.
- Drying time before painting: 48 hours (after complete drying).
- Adhesion: >0.8 MPa in accordance with EN 16566.

PRECAUTIONS FOR USE.

The temperature on application and during drying must be between +5°C and +35°C.

Do not apply at humidity levels of above 80%.

Do not apply to damp substrates.

WOOD FILLER must be covered.

On untreated wood, apply a primer beforehand.

PREPARATION OF SUBSTRATES.

Substrates must comply with DTUs, i.e. be clean, dry, hard, cohesive, healthy, dust-free and free of any trace of formwork oil.

APPLICATION THICKNESS.

Max 10 mm.

TYPE OF APPLICATION.

Applied by hand using a filling knife or spatula.

Clean tools with a dry cloth or with water if necessary.

DRYING TIME.

This depends on the ambient conditions, the type of substrate and the thickness of application.

A second coat, 1 mm thick, can be applied 12 hours after the first coat under normal conditions.

STORAGE.

12 months in the original, unopened packaging, protected from frost and high temperatures.



USAGE



APPLICATION

AFNOR NFT 36.005 classification: Family IV, class 4b

SEMIN

1a, rue de la Gare - F-57920 KEDANGE-SUR-CANNER
Tél. +33 (0)3.82.83.53.57 - Fax : +33 (0)3.82.83.93.33

www.semin.com



VOC content <1 g/L



MADE IN FRANCE

