



SEM-WOOD

WOOD FILLER POWDER POWDER FILLER INTERIOR-EXTERIOR

- + LITTLE SHRINKAGE
- + QUICK DRYING
- + GOOD LOAD-BEARING CAPACITY
- + EASY TO SAND

TECHNICAL DEFINITION.

Powdered filling and repair plaster for treating holes and cracks in wood.

Can also repair broken corners or reconstitute missing parts.

COMPOSITION AND APPEARANCE.

Plaster, mineral filler, resin and various additives.

The resulting paste is brown.

ACCEPTED SUBSTRATES.

All types of wood.

COVERING.

All types of paint, varnish and wood stain.

DOCUMENTS TO CONSULT.

- DTU 59.1: Building painting work
- EN 16566: paint plasters for interior work

TECHNICAL CHARACTERISTICS.

- Use temperature: 30 minutes.
- Second application: 3 hours, depending on the work.
- Drying time before painting: 24-48 hours (after complete drying).
- Adhesion: >0.8 MPa in accordance with EN 16566.

PRECAUTIONS FOR USE.

The temperature on application and during drying must be between +5°C and +35°C.

Do not apply at humidity levels of above 80%.

Do not apply to damp substrates.

WOOD FILLER must be covered.

On untreated wood, apply a primer beforehand.

PREPARATION OF SUBSTRATES.

Substrates must comply with DTUs, i.e. be clean, dry, hard, cohesive, healthy, dust-free and free of any trace of formwork oil.

MIXING PROPORTIONS.

0.4 l. water for 1 kg.

APPLICATION THICKNESS.

Any thickness.

TYPE OF APPLICATION.

Applied by hand using a filling knife or spatula.

Clean tools with a dry cloth or with water if necessary.

DRYING TIME.

It depends on the ambient conditions, the type of substrate and the thickness of application.

A second coat, 5 mm thick, can be applied 3 hours after the first coat under normal conditions.

STORAGE.

12 months in the original, unopened packaging, protected from frost and high temperatures.



USAGE



APPLICATION

AFNOR NFT 36.005 classification: Family IV class 4c

SEMIN

1a, rue de la Gare - F-57920 KEDANGE-SUR-CANNER
Tél. +33 (0)3.82.83.53.57 - Fax: +33 (0)3.82.83.93.33

www.semin.com



VOC content <1 g/L



MADE IN FRANCE

