



SEMIN 2 en 1 G&L

AIRLESS FILLING AND SMOOTHING COATING

- + HIGH FILLING POWER.
- + VERY GOOD SLIDE
- + VERY GOOD OPEN TIME.
- + EASY TO SAND

TECHNICAL DEFINITION.

Airless filling and smoothing coating. White finish, matt aspect, smoothed. Odourless. Low dust volatility and easy dust removal.

COMPOSITION AND APPEARANCE.

Solvents: Water.

Filler: Calcium carbonates.

Adjuvants: Dispersant, bactericide fungicide.

Thickeners: Cellulose fibres, polyacrylates.

Binders: Acrylic dispersant.

Density: 1.73.

Dry extract: 71%.

SUITABLE SUBSTRATES.

Ideal for smoothing plaster, plaster blocks and plaster boards. Concrete and slabs.

Painted surfaces.

COATING.

All types of coatings, paints and wall coverings.

TECHNICAL PROPERTIES.

· Film thickness: 0 to 4 mm.

· Fire classification: A2-S1, d0.

· VOC: <1 g/L.

PRECAUTIONS FOR USE.

Do not apply at a temperature lower than 8°C and above 35°C and relative humidity higher than 70%

Do not apply to overheated substrates.

Do not apply to damp substrates.

Regulations in force: EN 16-566: paint coatings for interior and/or exterior work.

NFT 36-005: characterisation of paint products.

SAFETY.

Ventilate the room and maintain good ventilation during spraying, application and drying of the product. Mask wearing is advised when spraying the product. In case of contact with eyes, rinse thoroughly with water.

PREPARATION OF SUBSTRATES.

The substrate must be prepared according to the DTU rules.

CONSUMPTION.

Smoothing, Raking, 800 g to 1.2 kg/m² per coat.

APPLICATION TYPE.

Airless application, the coating can be sprayed using any type of machine suitable for spraying coatings in 1 or 2 smooth passes. We recommend removing the filters and spraying at about 60 cm from the substrate.

Tools: Airless pump with stainless ball bearing (Ideal nozzles, 631 for smoothing or 635 to 651 according to the power of the machine used).

Clean tools with water.

DRYING TIME.

From 6 to 12 hours depending on the temperature, humidity and ventilation of the room.

PACKAGING.

10 kg and 25 kg buckets.

25 kg bag.

STORAGE.

18 months in unopened original container, away from frost and heat.



MECHANICAL APPLICATION




MECHANICAL APPLICATION

SEMIN

1a, rue de la Gare - F-57920 KEDANGE-SUR-CANNER

Tel. +33 (0)3.82.83.53.57 - Fax: +33 (0)3.82.83.93.33

www.semin.com



MADE IN FRANCE

